

AD-A128 751


ORDERING AND PLASTIC DEFORMATION IN ZIRCONIA BASED
CERAMICS(U) CASE WESTERN RESERVE UNIV CLEVELAND OH DEPT
OF METALLURGY AND... T E MITCHELL ET AL. 01 MAY 83
ARO-16667.1-MS DAAG29-80-C-0023

1/1

UNCLASSIFIED

F/G 11/2

NL




END

DATE

FILMED

DTIC



MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

ARO 16667.1-MS

(12)

AD A128751

ORDERING AND PLASTIC DEFORMATION IN ZIRCONIA-BASED CERAMICS

Final Report

T. E. Mitchell and A. H. Heuer

May 1983

U. S. Army Research Office
Contract DAAG29 80 C 0023

Department of Metallurgy and Materials Science
Case Western Reserve University
Cleveland, Ohio 44106

Approved for Public Release
Distribution Unlimited

DMC FILE COPY

DMC
LECTER
1981 1983
A

83 06 01 025

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
	DA128 751	
4. TITLE (and Subtitle) Ordering and Plastic Deformation in Zirconia based Ceramics		5. TYPE OF REPORT & PERIOD COVERED Final Report 12/1/79 - 11/30/82
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) T. E. Mitchell and A. H. Heuer		8. CONTRACT OR GRANT NUMBER(s) DAAG 29 80 C 0023
9. PERFORMING ORGANIZATION NAME AND ADDRESS Dept. of Metallurgy & Materials Science Case Western Reserve University Cleveland, Ohio 44106		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
11. CONTROLLING OFFICE NAME AND ADDRESS U. S. Army Research Office Post Office Box 12211 Research Triangle Park, NC 27709		12. REPORT DATE 5/1/83
		13. NUMBER OF PAGES
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES The view, opinions, and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) ceramics, zirconia, ordering, deformation		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Various aspects of phase transformations and deformation of ZrO_2 -CaO and ZrO_2 - Y_2O_3 ceramics have been studied. The kinetics of precipitation of both tetragonal (t- ZrO_2) and $CaZr_4O_9$ (ϕ_1) from cubic ZrO_2 -CaO solid solutions have been studied. The precipitation and growth of the precipitates proceed by nucleation and growth and quantitative analysis shows good agreement with data		

DD FORM 1 JAN 73 1473

EDITION OF 1 NOV 65 IS OBSOLETE

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

Statement of Problem

Zirconia-based ceramics are finding increasing applications in diverse areas where high toughness is required. The present research program was undertaken to investigate some poorly understood aspects of their structure. One area was the structure of the cubic solid solution and its decomposition into tetragonal and ordered phases. The other was the deformation behavior and the nature of dislocations in zirconia.

Summary of Results

(a) Precipitation in Ca-Stabilized Zirconia.

The initial phase of this work is best described in terms of the Abstract of the Ph.D. Thesis of J. M. Marder.

The kinetics of precipitation of both tetragonal zirconia (ZrO_2) and CaZr_4O_9 (ϕ_1) from cubic calcia-stabilized zirconia solid solutions were studied using transmission electron microscopy (TEM). A hypo-eutectoid (8.5 mole % CaO) hot-pressed polycrystal was used to investigate precipitation of tetragonal zirconia, and a hyper-eutectoid (16 mole % CaO) single crystal was used to investigate precipitation of ϕ_1 . The hypo-eutectoid material could not be quenched rapidly enough from the solution treatment temperature to retain the cubic solid solution; 1-2 nm particles of tetragonal ZrO_2 were present in quenched samples. Therefore, the precipitation of tetragonal particles could not be characterized from the nucleation stage. The coarsening of tetragonal particles proceeded by diffusional growth following the Greenwood-Lifshitz-Slyozov-Wagner (GLSW) theory, with an apparent activation energy of 425 kJ/mole, close to the activation energy for diffusion of calcium and zirconium in calcia-stabilized zirconia. The interfacial energy between the cubic solid solution and the tetragonal precipitates was estimated from the GLSW theory as 0.5 J/m^2 .

Fine particles generally retained tetragonal symmetry upon cooling to room temperature. However, after extended annealing treatments at 1300°C and 1400°C, some of the coarse particles transformed to either monoclinic zirconia, or to a new phase, designated zeta (ζ). Zeta phase may arise as a result of strain-induced transformation during specimen preparation, or may possibly be a transformation product that developed during cooling from the annealing temperature.

The precipitation and growth of ϕ_1 proceeded by nucleation and diffusional growth, and an isothermal transformation (IT) diagram showing the time required for initiation of the reaction as a function of annealing temperature was constructed. The activation energy for ϕ_1 coarsening was estimated from the GLSW theory to be 390 kJ/mole, essentially the same as that for the coarsening of tetragonal zirconia precipitates and also corresponding to the diffusion of calcium and zirconium. The interfacial energy between the cubic solid solution and ϕ_1 was approximately 0.2 J/m². The space group of ϕ_1 was determined through the use of convergent beam electron diffraction (CBD) to be C2/c, identical to CaHf₄O₉.

Prominent diffuse scattering originated from the cubic solid solution in both hypo- and hyper-eutectoid materials. In hyper-eutectoid material, the diffuse intensity sharpened into discrete ϕ_1 reflections but was still present in hypo-eutectoid material after precipitation of tetragonal ZrO₂. The origin of diffuse scattering in the latter case is not fully understood.

This work was followed by studying the stability of the ϕ_1 phase in CSZ single crystals containing 16-20 mol % CaO. Heat treatment at 1200°C and subsequent analysis by TEM has shown that the ϕ_1 -CaZr₄O₉ is metastable and is gradually replaced by ϕ_2 -Ca₆Zr₁₉O₄₄. There are two factors involved in explaining

why ϕ_1 forms first: it has a lower CaO content and it has a lower coherency strain with the cubic matrix.

The latest diagram due to Stubican and Hellman (Mat. Res. Bull. 17, 459, 1982) is shown in Fig. 1. Our findings show that in specimens of 17-19 m/o CaO, ϕ_1 transforms to ϕ_2 within 50-100 hours of annealing at 1200°C is in clear disagreement with the predictions of Fig. 1. Diffraction patterns illustrating the transformation are shown in Fig. 2. The strain contrast from ϕ_2 precipitates is illustrated in Fig. 3, which also shows alignment along $\langle 100 \rangle$ due to elastic interactions. Details are given in the preprint in Appendix 1.

(b) Phase Stability in $\text{ZrO}_2\text{-Y}_2\text{O}_3$

Y_2O_3 stabilizes the cubic phase field of ZrO_2 as do CaO and MgO. However, there are some interesting differences. We have discovered that single crystals of 6-8 w/o Y_2O_3 material are almost 100% tetragonal. Microstructural and microchemical analysis using analytical electron microscopy has shown that this tetragonal phase (which we call t') has a high Y_2O_3 content and is metastable. Annealing causes the t' to transform into the low Y_2O_3 tetragonal phase (t) plus cubic. The t phase occurs in the form of colonies of two tetragonal variants separated by low energy coherent twin boundaries. We postulate that the t' phase forms directly from the high temperature cubic phase by a massive transformation.

(c) Plastic Deformation of Calcia Stabilized Zirconia

The earlier stages of this research are summarized in the Abstract of the M.S. Thesis of C. E. Voegelé.

Single crystals of hypereutectoid CSZ were deformed between 1300°C and 1800°C along $[\bar{1}23]$, $[001]$, and $[\bar{1}33]$ compression axes in order to study primary, secondary, and duplex slip. Using slip trace analysis techniques, the primary $\{001\}\langle 110 \rangle$ system was confirmed, and the secondary slip system was determined to be $\{111\}\langle 1\bar{1}0 \rangle$. Little plastic anisotropy was found between the systems. Long

glide dislocations were observed at small strains, while uniform tangles of climbing dislocations were seen at large strains.

Single crystals of hypoeutectoid CSZ, aged prior to deformation to produce tetragonal precipitates, were considerably stronger than their unaged counterparts. Single crystals of hypereutectoid CSZ, containing CaZr_4O_9 precipitates prior to deformation, were also studied and found to be stronger than their unaged counterparts. The precipitates and dislocations in both the hypo- and hypereutectoid crystals were imaged; however, more work must be done in this area in order to fully characterize the precipitate-dislocation interactions.

Further studies of precipitation hardening due to tetragonal in hypoeutectoid and ϕ_1 in hypereutectoid have been undertaken. Fig. 4 shows stress strain curves that demonstrate the existence of strong precipitation hardening in hypereutectoid material. TEM was performed on foils cut parallel to the (001) slip plane. Fig. 5 shows that dislocations are concentrated in channels surrounded by precipitates which exhibit a high strain contrast. The channels are free of precipitates, implying that the precipitates are sheared by the dislocations and subsequently dissolve. Fig. 6 shows a series of micrographs taken under different imaging conditions where there are precipitates in the lower left and dislocations and relatively few precipitates in the upper right. Fig. 6(a) is a WBDF picture showing both precipitates and dislocations. Fig. 6(b) is a DF picture showing precipitates only. Fig. 6(c) is a BF picture showing the matrix strain contrast. Fig. 6(d) is a WBDF picture showing dislocations in the matrix. This is the first observation of dislocation channeling in a ceramic system although it has been observed previously in some metallic alloys and irradiated metals. In conclusion, this research has been highly successful and accomplished essentially all that was proposed. Two students obtained theses from the research and a good start was made by two others. Fortunately they were able to transfer two reasonably well-related projects and so this important research area will continue to be investigated.

Publications

J. M. Marder, T. E. Mitchell and A. H. Heuer, "Precipitation From Cubic ZrO_2 Solid Solutions", Acta Met. 31, 387 (1983).

J. M. Marder, A. H. Heuer and T. E. Mitchell, "Kinetics of Precipitation in Calcia Stabilized Zirconia", Phase Transformation, H. I. Aaronson, ed., p. 727 (1983).

J. W. Hangan, T. E. Mitchell and A. H. Heuer, "Precipitation of ϕ_1 - $CaZr_4O_{99}$ and ϕ_2 - $Ca_6Zr_{19}O_{44}$ in Calcia-Stabilized Zirconia", Electron Microscopy Soc. of Amer. Proceedings, in press (1983).

An additional publication is being prepared for the Zirconia Conference in Stuttgart (May 1983) and the work on plastic deformation is also in preparation.

Participating Scientific Personnel

1. J. M. Marder, Ph.D. (1982).
2. C. E. Voegelé, M.S. (1982).
3. V. Lanteri, did not finish Ph.D. while being supported on the Army Contract but will complete thesis on ZrO_2 - Y_2O_3 in 1984.
4. J. W. Hangan, did not finish M.S. while being supported on the Army Contract but will complete thesis on plastic deformation in 1983.

APPENDIX 1. From Proceedings of the Electron Microscopy Society of America, G. W. Bailey, ed., Claitor's, in press (1983).

PRECIPITATION OF ϕ_1 -CaZr₄O₉₉ and ϕ_2 -Ca₆Zr₁₉O₄₄ IN CALCIA-STABILIZED ZIRCONIA

J. W. Hangan, T. E. Mitchell and A. H. Heuer

Department of Metallurgy and Materials Science
Case Western Reserve University, Cleveland, Ohio 44106

INTRODUCTION. CaO stabilizes the high temperature cubic phase field of ZrO₂ resulting in an eutectoid reaction at 1140°C, as shown in Fig. 1 [1]. Two ordered defect structures are known to occur in the zirconia-calcia system on the hypereutectoid side of the cubic phase field. One is a monoclinic precipitate called ϕ_1 with the composition of CaZr₄O₉, whereas the other is a rhombohedral precipitates (R3c) called ϕ_2 which has a composition of Ca₆Zr₁₉O₄₄ [1]. The names of the precipitates are derived from analogous structures in the calcia-hafnia system, and these structures are described by Allpress, et al. [2]. The present study has been designed to use TEM to describe the microstructures more fully.

EXPERIMENTAL. Single crystals of calcia-stabilized zirconia (CSZ) of 16-20m/o were heat treated in air from 20-100 hr at 1200°C. Foils were prepared by ion-thinning, and their composition and microstructure were analyzed on a Phillips EM400T analytical electron microscope.

RESULTS. Fig. 2a is a [110] zone axis diffraction pattern of a 17m/o specimen aged for 20 hr at 1200°C which shows both ϕ_1 and ϕ_2 precipitate reflections. Fig. 2b is a diffraction pattern of the same zone axis in another specimen of the same composition aged for 100 hr at 1200°C which shows only ϕ_2 reflections; all the ϕ_1 has transformed to ϕ_2 . This shows that ϕ_1 is metastable in the composition range of 17m/o, whereas the phase diagram prepared by the reactive gel process in Fig. 1 predicts that it should be stable.

The ϕ_1 precipitates in Fig. 3a are approximately 90-130nm long after being aged for 336 hr at 1200°C in a crystal of 16m/o CSZ [3]. The precipitates are equiaxed, and mostly randomly distributed, although they do form some random clusters. The ϕ_2 precipitates in Fig. 3b were grown for 100 hr at 1200°C in 17m/o CSZ. They are 25 nm wide and tend to align themselves along $\langle 100 \rangle_c$ directions to relieve the high coherency strains which cause high strain contrast in bright field. The ϕ_1 precipitates exhibit less strain contrast and have less tendency to align themselves along $\langle 100 \rangle_c$ directions. Both Figures 3a and 3b were taken near a $\langle 100 \rangle_c$ zone axis.

DISCUSSION. The existence of the ϕ_1 and ϕ_2 phases is not completely understood. However, the present results show that ϕ_1 may be a metastable phase due to the high coherency strains that could make ϕ_2 to nucleate, as well as the fact that it contains more calcia than ϕ_1 . This work has shown the usefulness of TEM in studying single crystals to serve as a check on phase diagrams prepared using finer grained processes.

REFERENCES

1. J.R.Hellmann and V.S.Stubican, Mat. Res. Bull., 17, 459 (1982).
2. J.G.Allpress, et al., J. Solid State Chem., 14, 264 (1975).
3. Specimen from J.M.Marder, T.E.Mitchell and A.H.Heuer, Acta Met., 31, 387 (1983). This work was supported by the Army Research Office.




Fig. 1. Zirconia-calcia phase diagram [1]. Specimen composition in this study are marked with crosses.

Fig. 2. $\langle 110 \rangle$ diffraction patterns from 17m/o crystals: (a) aged 20 hr showing both ϕ_1 and ϕ_2 reflections in the fcc matrix, the former being stronger than the latter; (b) aged for 100 hr showing only ϕ_2 reflections, the metastable ϕ_1 having transformed to ϕ_2 .





Fig. 3a. DF of ϕ_1 precipitate in 16m/o CSZ aged for 336 hr at 1200°C.



Fig. 3b. DF of ϕ_2 precipitate in 17m/o CSZ aged for 100 hr at 1200°C. Note the tendency to align along $[001]$.




Fig. 1. ZrO_2 rich portion of the ZrO_2 - CaO phase diagram, from Stubican and Hellman.




Fig. 2. Diffraction patterns from ZrO_2 -17m/o CaO : left (aged 20 hrs at 1200°C) mostly ϕ_1 ; right (aged 100 hrs) only ϕ_2 . Top to bottom are [111], [110] and [112] zones respectively.

Reproduced from
best available copy.




Fig. 3. ϕ_2 precipitates imaged in DF showing strong tendency to align along $\langle 100 \rangle$.




Fig. 4. Stress-strain curves of unaged (cubic) and aged (cubic + ϕ precipitates) hypereutectoid crystals showing strong precipitation hardening.



Fig. 5. Precipitate-free channel containing dislocations in aged and deformed hyperstoichiometric crystal.

Reproduced from
best available copy.



Fig. 6. Aged and deformed hyperstoichiometric crystal: (a) WBDF of ϕ and dislocations, (b) DF of ϕ only, (c) BF of matrix strain contrast, (d) WBDF of dislocations only.

Reproduced from
best available copy.